

THREADLOCKER - TWO-PART EPOXY

JET-LOK III is a two-part zinc-free epoxy, with largely non-metallic fillers, that can be used to permanently lock threaded connections under normal operating conditions.







Both the handy-pak and kit use a new catalyst for added pot life and durability with lower toxicity and less heat generation making it the optimum choice for any application. It is designed for use on all threaded joints or fasteners where an exceptionally strong and durable bond is required. It is especially useful on drilling tools, casing, and other tubulars where the effective prevention of joint loosening is required.

The catalyst is emptied into the container containing the base epoxy resin, where the two are thoroughly mixed. The applicator is used to completely cover the male threads with the mixture and the joint is then coupled. The catalyst/hardener when stirred homogeneously into the resin results in a pot life of the mixture under average conditions of 25-75 minutes, during which time it remains in a workable consistency. The mixture of the resin and catalyst also result in lower exotherm, temperatures stay below 66°C, so safer for the user. The resin is cured and the connection ready for service in 4-6 hours. The cure time can be reduced by elevating the temperature up to 121°C and increased by spreading to a thinner film to reduce the heat generated by the reaction.



THREADLOCKER - TWO-PART EPOXY

APPLICATIONS

- Recommended for use on casing, shoes, couplings, sub savers, towing eyes and collars; eliminating the need for gas/arc welding
- Threadlock Handy-Pak and Kit offer a distinct advantage over welding in that threaded connections may be broken out by heating to 288°C
- This product is also excellent for any application requiring a strong, permanent bond that has high vibration resistance. Being free of zinc enhances its durability in wet services.

BENEFITS

- Complete Resin and Activator Handy-Pak and Kit - 68 ML and 255 ML
- Noncorrosive
- Economical
- Adheres to any clean surface
- Good for service up to 204°C
- Ease of application
- Prevents back-off
- Resistant to acids, solvents, and water
- One JET-LOK III handy-pak will coat one 13-3/8 connection with almost zero waste.

Typical Characteristics		
Colour	Grey	
Density (lb/gal)	13.16	
Specific Gravity	1,56	
Flash Point	221°C	
Work Life (typical)	120-180 minutes	
Maximum Exotherm	66°C	
Temperature Stability	204°C	
Friction Factor		
Rotary Shouldered Connections	0.9 - 1.0	
*Noninterference (T&C)	1.3 - 2.0	
Lap Shear Strength	2500 to 3100 psi	

^{*} Friction factors and coefficients of friction can be affected by many factors such as total surface movement under load, contact pressure, thread design parameters, temperature and hydraulic cell development due to trapping of product in the threads.

Casing O.D. (inches)	Approx. # of Joints Per Kit (255 ML)
4 1/2	5
5 ½	3
6 ½ - 7	2
7 % - 9%	2
10 ¾ - 13 ⁵ ⁄ ₇	1

CAUTION:

Prolonged, over exposure could result in skin and eye irritation or sensitization. Mix in well-ventilated area. Use rubber or plastic gloves and goggles when mixing for application. Practice reasonable care and cleanliness when using this product. For persons with hypersensitive skin, wash hands and face thoroughly with soap and water after completion of job. If material enters eyes, flush with water immediately and seek medical care.

PACKAGING:

Durable, corrosion resistant plastic spool, locked into a matching shell.

Product #	Product	# per box	Size
1710557	Glue kit Jet Lok III HANDY-PAK	24	68ml
	(Resin & Activator)		
	Glue kit Jet Lok III		
1710558	jar & bottle	12	255ml
	(Resin & Activator)		

